



BIOTECH TESTING SERVICES LLP



NABL Scope



TC - 8484

TEST REPORT

REPORT NO. : BTS2503594-01

DATE : 31-12-2025

ULR NO. : TC848425100001458F

NAME OF CUSTOMER : STYLM INDUSTRIES LIMITED

ADDRESS : SCO 14, Sector 7C
Madhya Marg
-160019
Chandigarh, India

REFERENCE : Reference Letter No. Nil dated November 26, 2025
Kind Attention: Nitish Kanwar

DATE OF RECEIPT : 27-11-2025

DATE OF INITIATION : 28-11-2025

DATE OF COMPLETION : 31-12-2025

SAMPLE DESCRIPTION :

Sample No.	Sample Details
2503594/S01	Sample-1
	<i>Description</i> <i>Stylam High Pressure Laminate</i>

BTS2503594-01
Page 1 of 5

• Samples are not drawn by the laboratory • Results relate only to the samples tested
• This report shall not be reproduced except in full without prior permission of this laboratory



BIOTECH TESTING SERVICES LLP



NABL Scope



TC - 8484

Name of Test :

ASTM G 21 - 21
Determining Resistance of Synthetic Polymeric Materials to Fungi

Test Organisms :

1. Mixed Spores Suspension

Experimental Conditions

Sample Size	: 50 mm x 50 mm
No of replicates	: Three
Viability Control	: Sterile Filter paper
Media used	: Nutrient Salt agar
Incubation Temperature	: 28°C ± 1°C
Humidity	: >85% Relative Humidity
Duration of Exposure	: 28 days

BTS2503594-01
Page 2 of 5

• Samples are not drawn by the laboratory • Results relate only to the samples tested
• This report shall not be reproduced except in full without prior permission of this laboratory



BIOTECH TESTING SERVICES LLP



NABL Scope



TC - 8484

Procedure:

Specimens of size 50 mms x 50 mms were placed on Nutrient salt agar. Composite spore suspension as listed below was sprayed on specimen. The Nutrient salt agar provides all of the trace nutritional elements needed by Fungi except Carbon source. Fungus grows only when it is able to use polymeric material as Primary carbon source. Inoculated samples were incubated and examined for fungal growth. Temperature and humidity were maintained for the duration of the test. Adequate positive and Negative controls were also included along with specimen.

Mixed spore suspension of -

1. Aspergillus niger ATCC 9642
2. Penicillium pinophilum ATCC 11797
3. Gliocladium virens ATCC 9645
4. Chaetobium globosum ATCC 6205
5. Aurobasidium pullulans ATCC 15233

Results:

Observations were made on weekly basis for appearance for the density of fungal growth. The filter paper control pieces had copious fungal growth at 2 weeks.

At 4th week, samples were rated "0" or "1" were examined microscopically to confirm the Ratings

Rating scale for the test is as follows:

Growth on specimen	Rating
None	0
Trace of Growth (< 10 %)	1
Light Growth (10 to 30 %)	2
Medium Growth (30 to 60 %)	3
Heavy Growth (60% to complete coverage)	4

Sample Identification	Duration of the test				
	Replicates	Week 1	Week 2	Week 3	Week 4
2503594/S01	Set I	0	0	0	0
	Set II	0	0	0	0
	Set III	0	0	0	0
Control	-	1	2	3	4

BTS2503594-01
Page 3 of 5

- Samples are not drawn by the laboratory
- Results relate only to the samples tested

• This report shall not be reproduced except in full without prior permission of this laboratory



BIOTECH TESTING SERVICES LLP



NABL Scope



TC - 8484

COMMENT:

Test sample labeled as **Stylam High Pressure Laminate** is **Resistant to fungal attack** at the end of 28 days of incubation when tested as per specified method.

***** *End of Report* *****



For Biotech Testing Services LLP

Dr. Shilpa U Nair
Quality Manager
(Authorized Signatory)

BTS2503594-01
Page 4 of 5

- Samples are not drawn by the laboratory
- Results relate only to the samples tested

• This report shall not be reproduced except in full without prior permission of this laboratory



BIOTECH TESTING SERVICES LLP




NABL Scope



TC - 8484

Annexure

2503594/S01	2503594/S01
	 Observation at 4 weeks

BTS2503594-01
Page 5 of 5

- Samples are not drawn by the laboratory
- Results relate only to the samples tested

• This report shall not be reproduced except in full without prior permission of this laboratory