

STYLAM HIGH PRESSURE LAMINATES - GLOSS PRO+

High Pressure Laminates (HPL) as per EN 438-2 & 3 : 2016, are available in the standard HGS/VGS and High gloss (Gloss Pro+) range.

| SR. NO. | Properties | Test Method | Attributes of Performance | Unit of Measurement | Results (As per EN 438-3) |
|------------|--|------------------------------|---|------------------------|---------------------------------|
| | | | EN-438 Laminate Classification | | HGS / VGS |
| 1 | SURFACE QUALITY | | | | |
| 1.1 | Surface quality | EN 438-2:2016 (Clause-4) | Spots, dirt and similar surface defects | mm²/m² | ≤1 |
| | | | Fibres, hairs and scratches | mm/m² | ≤ 10 |
| 2 | DIMENSIONAL PROPERTIES | | | | |
| 2.1 | Thickness | EN 438-2:2016 (Clause-5) | Thickness tolerance | mm mm | 0.5≤T<1 : ±0.1 1≤T<2 : ±0.15 |
| 2.2 | Size | EN 438-2:2016 (Clause-6) | Length and width | mm | + 10 / - 0 |
| 2.3 | Straightness of edges | EN 438-2:2016 (Clause-7) | Straightness of edges | mm/m | ≤ 1.5 |
| 2.4 | Squareness | EN 438-2:2016 (Clause-8) | Squareness | mm/m | ≤ 1.5 |
| 2.5 | Flatness | EN 438-2:2016 (Clause-9) | Flatness (measured on full-size sheet) | mm/m | 60 |
| 3 | PHYSICAL PROPERTIES | | | | |
| 3.1 | Resistance to surface wear | EN 438-2:2016 (Clause-10) | Wear Resistance - Initial Point | Revolutions | ≥ 150 (HGS) / ≥ 50 (VGS) |
| 3.2 | Resistance to immersion in boiling water | EN 438-2:2016 (Clause-12) | Appearance | Rating | ≥ 3 |
| 3.3 | Resistance to water vapour | EN 438-2:2016 (Clause-14) | Appearance | Rating | ≥ 3 |
| 3.4 | Resistance to dry heat (160°C) | EN 438-2:2016 (Clause-16) | Appearance | Rating | ≥ 3 |
| 3.5 | Dimensional stability at elevated temperatures | EN 438-2:2016 (Clause-17) | Cumulative dimensional change - | Longitudinal % | ≤ 0.55 (HGS) / ≤ 0.75 (VGS) |
| | | | | Transversal % | ≤ 1.05 (HGS) / ≤ 1.25 (VGS) |
| 3.6 | Resistance to Wet Heat | EN 438-2:2016 (Clause-18) | Appearance | Rating | ≥3 |
| 3.7 | Resistance to impact with Small diameter ball | EN 438-2:2016 (Clause-20) | Spring Force | Ν | ≥ 20 (HGS) / ≥ 15 (VGS) |
| 3.8 | Resistance to cracking under stress | EN 438-2:2016 (Clause-23) | Appearance | Rating | ≥ 4 |
| 3.9 | Resistance to scratching | EN 438-2:2016 (Clause-25) | Appearance - Smooth Finish | Rating | ≥ 2 (HGS) / ≥1 (VGS) |
| 3.10 | Resistance to staining | EN 438-2:2016 | Appearance - Group 1 & 2 | Rating | ≥5 |
| 2.20 | | (Clause-26) | Appearance - Group 3 | Rating | ≥ 4 |
| 3.11 | Light fastness (Xenon arc) | EN 438-2:2016 (Clause-27) | Contrast | Grey scale rating | 4 to 5 |
| 3.12 | Density | EN ISO 1183-1 | Density | gm/cm³ | ≥ 1.35 |
| 3.13 | Gloss Level | DIN 67530 | Gloss Level @ 60° | GU | ≥ 90 |
| 3.14 | DOI Value | RHO Point meter | DOI value | Level | ≥ 90 |
| 3.15 | | RHO Point meter | RIQ value | Level | ≥ 80 |
| 3.16 | Tape resistance | IHD-W-464 | Adhesion test (cross cut) | Rating | 0 |

Disclaimer:

Stylam HPL complies with the applicable standards as listed above, but the results may vary due to difference in application of product. STYLAM reserves the right to change product composition and characteristics.